

Woodtype	<b>ASH</b>
Description	3 layers of the same hardwood. The Ash without heartwood has a light yellow to slightly brownish colour. The sorting Auslese is essentially knot-free*, with a simple structure.
Brinell hardness	4,5 kp
Gross density	0,69 g   cm <sup>3</sup>

## 1-Strip Country House Flooring ASH Auslese "St.Pölten"



### Surfaces


- Oil | wax oxidative dried
- Varnished 7-times
- Untreated sanded
- Brushed
- Bevel
- Special colour



Symbol picture - may vary in colour and structure

Sorting guidelines	Auslese
Healthy knots	till ø 5 mm allowed
Black knots	till ø 5 mm allowed
Healthy red heart	not allowed
Healthy heartwood	not allowed
Cracks	not allowed
Curled spots   differences in structure	scattered allowed
Natural differences in colour	slightly allowed
Natural fiber orientation	scattered allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	not allowed
Stains from storage and light blueness	not allowed
Knocked spots	not allowed
Mirror	not allowed

Technical data	
Thickness:	15 mm <span style="background-color: #e0e0e0;">Useful layer: approx. 5 mm</span>
Width:	150 mm
Length:	Lengthsystem 6 layers 1900 mm (8 layers   pkg.) 2 layers 950 mm*
Connection:	Tongue and groove <small>One layer 950 mm consists of 2 boards*</small>
m <sup>2</sup>   pkg.	2,28
m <sup>2</sup>   pal.	111,72
kg   pkg.	23
kg   pal.	1127
<input checked="" type="checkbox"/>	Floating laying
<input checked="" type="checkbox"/>	Glued laying
<input checked="" type="checkbox"/>	<b>Suitable for underfloor heating</b> <small>when gluing the entire area with solvent-free adhesives</small>




Woodtype	<b>ASH</b>
Description	3 layers of the same hardwood. The Ash without heartwood has a light yellow to slightly brownish colour. The sorting Wohngefühl is knotty, with a medium structure.
Brinell hardness	4,5 kp
Gross density	0,69 g   cm <sup>3</sup>

## 1-Strip Country House Flooring ASH Wohngefühl "Eisenstadt"



### Surfaces

- Oil | wax oxidative dried
- Varnished 7-times
- Untreated sanded
- Brushed
- Bevel
- Special colour



Symbol picture - may vary in colour and structure

Sorting guidelines	Wohngefühl
Healthy knots	allowed (partly filled)
Black knots	to approx. 35 mm allowed (partly filled)
Healthy red heart	not allowed
Healthy heartwood	not allowed
Cracks	scattered allowed (partly filled)
Curled spots   differences in structure	scattered allowed
Natural differences in colour	allowed
Natural fiber orientation	to max. 1   3 allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	scattered allowed
Stains from storage and light blueness	not allowed
Knocked spots	not allowed
Mirror	not allowed

Technical data	
Thickness:	15 mm <span style="background-color: #e0e0e0;">Useful layer: approx. 5 mm</span>
Width:	150 mm
Length:	Lengthsystem 6 layers 1900 mm (8 layers   pkg.) 2 layers 950 mm*
Connection:	Tongue and groove <small>One layer 950 mm consists of 2 boards*</small>
m <sup>2</sup>   pkg.	2,28
m <sup>2</sup>   pal.	111,72
kg   pkg.	23
kg   pal.	1127
<input checked="" type="checkbox"/>	Floating laying
<input checked="" type="checkbox"/>	Glued laying
<input checked="" type="checkbox"/>	Suitable for underfloor heating <small>when gluing the entire area with solvent-free adhesives</small>



Woodtype	<b>ASH</b>
Description	3 layers of the same hardwood. The Ash without heartwood has a light yellow to slightly brownish colour. The sorting Wohngefühl is knotty, with a medium structure.
Brinell hardness	4,5 kp
Gross density	0,69 g   cm <sup>3</sup>

## 1-Strip Country House Flooring ASH Wohngefühl "Eisenstadt" B190



### Surfaces

- Oil | wax oxidative dried
- Varnished 7-times
- Untreated sanded
- Brushed
- Bevel
- Special colour



Symbol picture - may vary in colour and structure

Sorting guidelines	Wohngefühl
Healthy knots	allowed (partly filled)
Black knots	to approx. 35 mm allowed (partly filled)
Healthy red heart	not allowed
Healthy heartwood	not allowed
Cracks	scattered allowed (partly filled)
Curled spots   differences in structure	scattered allowed
Natural differences in colour	allowed
Natural fiber orientation	to max. 1   3 allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	scattered allowed
Stains from storage and light blueness	not allowed
Knocked spots	not allowed
Mirror	not allowed

Technical data					
Thickness:	15 mm <span style="background-color: #e0e0e0;">Useful layer: approx. 5 mm</span>				
Width:	190 mm				
Length:	Lengthsystem 5 layers 1900 mm (6 layers   pkg.) 1 layer 950 mm*				
Connection:	Tongue and groove <small>One layer 950 mm consists of 2 boards*</small>				
<table border="1" style="width: 100%;"> <tr> <td>m<sup>2</sup>   pkg. 2,17</td> <td>m<sup>2</sup>   pal. 97,65</td> </tr> <tr> <td>kg   pkg. 22</td> <td>kg   pal. 990</td> </tr> </table>		m <sup>2</sup>   pkg. 2,17	m <sup>2</sup>   pal. 97,65	kg   pkg. 22	kg   pal. 990
m <sup>2</sup>   pkg. 2,17	m <sup>2</sup>   pal. 97,65				
kg   pkg. 22	kg   pal. 990				
<input checked="" type="checkbox"/> Floating laying <input checked="" type="checkbox"/> Glued laying <input checked="" type="checkbox"/> Suitable for underfloor heating <small>when gluing the entire area with solvent-free adhesives</small>					



Woodtype	<b>ASH</b>
Description	3 layers of the same hardwood. The Ash with heartwood has a light yellow to slightly brownish to prominent dark brown colour. The sorting Design is slightly to very knotty, with a lively structure.
Brinell hardness	4,5 kp
Gross density	0,69 g   cm <sup>3</sup>


## 1-Strip Country House Flooring ASH Design "Melk"



with heartwood

### Surfaces

- Oil | wax oxidative dried
- Varnished 7-times
- Untreated sanded
- Brushed
- Bevel
- Special colour



### Also available as

- System board  
(Fixlength 1100 mm)
- Kreativ 10,7 mm



Symbol picture - may vary in colour and structure

Sorting guidelines	Design
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	allowed
Healthy heartwood	allowed
Cracks	allowed (partly filled)
Curled spots   differences in structure	allowed
Natural differences in colour	allowed
Natural fiber orientation	allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	not allowed

Technical data					
Thickness:	15 mm <span style="background-color: #e0e0e0;">Useful layer: approx. 5 mm</span>				
Width:	150 mm				
Length:	Lengthsystem 6 layers 1900 mm (8 layers   pkg.) 2 layers 950 mm*				
Connection:	Tongue and groove <small>One layer 950 mm consists of 2 boards*</small>				
<table border="0" style="width: 100%;"> <tr> <td style="border: 1px solid black; padding: 5px;">m<sup>2</sup>   pkg. 2,28</td> <td style="border: 1px solid black; padding: 5px;">m<sup>2</sup>   pal. 111,72</td> </tr> <tr> <td style="border: 1px solid black; padding: 5px;">kg   pkg. 23</td> <td style="border: 1px solid black; padding: 5px;">kg   pal. 1127</td> </tr> </table>		m <sup>2</sup>   pkg. 2,28	m <sup>2</sup>   pal. 111,72	kg   pkg. 23	kg   pal. 1127
m <sup>2</sup>   pkg. 2,28	m <sup>2</sup>   pal. 111,72				
kg   pkg. 23	kg   pal. 1127				
<ul style="list-style-type: none"> <li><input checked="" type="checkbox"/> Floating laying</li> <li><input checked="" type="checkbox"/> Glued laying</li> <li><input checked="" type="checkbox"/> Suitable for underfloor heating <small>when gluing the entire area with solvent-free adhesives</small></li> </ul>					






Woodtype	<b>ASH</b>
Description	3 layers of the same hardwood. The Ash with heartwood has a light yellow to slightly brownish to prominent dark brown colour. The sorting Design is slightly to very knotty, with a lively structure.
Brinell hardness	4,5 kp
Gross density	0,69 g   cm <sup>3</sup>

## 1-Strip Country House Flooring ASH Design "Melk" B190



### Surfaces

- Oil | wax oxidative dried
- Varnished 7-times
- Untreated sanded
- Brushed
- Bevel
- Special colour



Symbol picture - may vary in colour and structure

Sorting guidelines	Design
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	allowed
Healthy heartwood	allowed
Cracks	allowed (partly filled)
Curled spots   differences in structure	allowed
Natural differences in colour	allowed
Natural fiber orientation	allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	not allowed

Technical data					
Thickness:	15 mm <span style="background-color: #e0e0e0;">Useful layer: approx. 5 mm</span>				
Width:	190 mm				
Length:	Lengthsystem 5 layers 1900 mm (6 layers   pkg.) 1 layer 950 mm*				
Connection:	Tongue and groove <small>One layer 950 mm consists of 2 boards*</small>				
<table border="0" style="width: 100%;"> <tr> <td style="border: 1px solid black; padding: 5px;">m<sup>2</sup>   pkg. 2,17</td> <td style="border: 1px solid black; padding: 5px;">m<sup>2</sup>   pal. 97,65</td> </tr> <tr> <td style="border: 1px solid black; padding: 5px;">kg   pkg. 22</td> <td style="border: 1px solid black; padding: 5px;">kg   pal. 990</td> </tr> </table>		m <sup>2</sup>   pkg. 2,17	m <sup>2</sup>   pal. 97,65	kg   pkg. 22	kg   pal. 990
m <sup>2</sup>   pkg. 2,17	m <sup>2</sup>   pal. 97,65				
kg   pkg. 22	kg   pal. 990				
<ul style="list-style-type: none"> <li><input checked="" type="checkbox"/> Floating laying</li> <li><input checked="" type="checkbox"/> Glued laying</li> <li><input checked="" type="checkbox"/> Suitable for underfloor heating <small>when gluing the entire area with solvent-free adhesives</small></li> </ul>					




Woodtype	<b>ASH</b>
Description	3 layers of the same hardwood. The Ash without heartwood has a light yellow to slightly brownish colour. The special feature are the natural colour differences. The sorting Ambiente is slightly to very knotty, with a medium structure.
Brinell hardness	4,5 kp
Gross density	0,69 g   cm³

## 1-Strip Country House Flooring ASH Ambiente City Star „Paris”



### Surfaces

- Oil | wax oxidative dried
- Varnished 7-times
- Untreated sanded
- Brushed
- Bevel
- Special colour



### Also available as

- 2-Lengthsystem
- Ladder optic
- Herringbone 475 mm
- Herringbone 950 mm



Symbol picture - can vary in colour and structure


Sorting guidelines	Auslese
Healthy knots	fill Ø 10 mm allowed (partly filled)
Black knots	fill Ø 10 mm allowed (partly filled)
Healthy red heart	not allowed
Healthy heartwood	not allowed
Cracks	not allowed
Curled spots   differences in structure	allowed
Natural differences in colour	allowed
Natural fiber orientation	allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	not allowed
Stains from storage and light blueness	not allowed
Knocked spots	not allowed
Mirror	not allowed

Technical data					
Thickness:	15 mm				
Width:	120 mm				
Length:	Lengthsystem* 5 layers 1900 mm				
	(8 Layers   Pkg.) 3 layers 950 mm**				
	Lengthsystem 6 layers 950 mm**				
	(8 Layers   Pkg.) 2 layers 475 mm***				
Connection:	Nuß und Feder One layer 950 mm consists of 2 boards** One layer 475 mm consists of 2 boards***				
<table border="1" style="width: 100%;"> <tr> <td>m²   Pkg. 1,83*   0,91</td> <td>m²   Pal. 89,67*   57,33</td> </tr> <tr> <td>kg   Pkg. 18*   9</td> <td>kg   Pal. 882*   567</td> </tr> </table>		m²   Pkg. 1,83*   0,91	m²   Pal. 89,67*   57,33	kg   Pkg. 18*   9	kg   Pal. 882*   567
m²   Pkg. 1,83*   0,91	m²   Pal. 89,67*   57,33				
kg   Pkg. 18*   9	kg   Pal. 882*   567				
<input checked="" type="checkbox"/> Floating laying <input checked="" type="checkbox"/> Glued laying <input checked="" type="checkbox"/> Suitable for underfloor heating when gluing the entire area with solvent-free adhesives					



Woodtype	<b>ASH steamed</b>
Description	3 layers of the same hardwood. The Ash without heartwood receives a brown colour due to the steaming with vitalized Grandeur water. The special feature is the white or black pore. The sorting Emotion is slightly knotty, with a lively structure.
Brinell hardness	4,5 kp
Gross density	0,69 g   cm <sup>3</sup>

## 1-Strip Country House Flooring steamed Emotion "Velden"



### Surfaces

- Oil | wax oxidative dried
- Brushed
- Pore black
- Pore white



Symbol picture - may vary in colour and structure

Sorting guidelines	Emotion
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	not allowed
Healthy heartwood	not allowed
Cracks	not allowed
Curled spots   differences in structure	allowed
Natural differences in colour	allowed
Natural fiber orientation	allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	not allowed

Technical data	
Thickness:	15 mm <span style="background-color: #e0e0e0;">Useful layer: approx. 5 mm</span>
Width:	150 mm
Length:	Lengthsystem 6 layers 1900 mm (8 layers   pkg.) 2 layers 950 mm*
Connection:	Tongue and groove <small>One layer 950 mm consists of 2 boards*</small>
m <sup>2</sup>   pkg.	2,28
m <sup>2</sup>   pal.	111,72
kg   pkg.	23
kg   pal.	1127
<input checked="" type="checkbox"/> Floating laying <input checked="" type="checkbox"/> Glued laying <input checked="" type="checkbox"/> Suitable for underfloor heating <small>when gluing the entire area with solvent-free adhesives</small>	



Woodtype	<b>ASH</b>
Description	3 layers of the same hardwood. The Ash without heartwood has a light yellow to slightly brownish colour. The special feature is the white or black pore. The sorting Emotion is slightly knotty, with a lively structure.
Brinell hardness	4,5 kp
Gross density	0,69 g   cm <sup>3</sup>

## 1-Strip Country House Flooring ASH Emotion "Pörtschach"



### Surfaces

- Oil | wax oxidative dried
- Brushed
- Pore black
- Pore white



Symbol picture - may vary in colour and structure

Sorting guidelines	Emotion
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	not allowed
Healthy heartwood	not allowed
Cracks	not allowed
Curled spots   differences in structure	allowed
Natural differences in colour	allowed
Natural fiber orientation	allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	not allowed

Technical data					
Thickness:	15 mm <span style="background-color: #e0e0e0;">Useful layer: approx. 5 mm</span>				
Width:	150 mm				
Length:	Lengthsystem 6 layers 1900 mm (8 layers   pkg.) 2 layers 950 mm*				
Connection:	Tongue and groove <small>One layer 950 mm consists of 2 boards*</small>				
<table border="0" style="width: 100%;"> <tr> <td style="border: 1px solid black; padding: 5px;">m<sup>2</sup>   pkg. 2,28</td> <td style="border: 1px solid black; padding: 5px;">m<sup>2</sup>   pal. 111,72</td> </tr> <tr> <td style="border: 1px solid black; padding: 5px;">kg   pkg. 23</td> <td style="border: 1px solid black; padding: 5px;">kg   pal. 1127</td> </tr> </table>		m <sup>2</sup>   pkg. 2,28	m <sup>2</sup>   pal. 111,72	kg   pkg. 23	kg   pal. 1127
m <sup>2</sup>   pkg. 2,28	m <sup>2</sup>   pal. 111,72				
kg   pkg. 23	kg   pal. 1127				
<input checked="" type="checkbox"/> Floating laying <input checked="" type="checkbox"/> Glued laying <input checked="" type="checkbox"/> Suitable for underfloor heating <small>when gluing the entire area with solvent-free adhesives</small>					





Woodtype	<b>ASH steamed</b>
Description	3 layers of the same hardwood. The Ash without heartwood receives an appealing dark brown colour due to the steaming with vitalized Grander water and the special treatment with oil   wax mocca brown. The sorting Emotion is slightly knotty, with a lively structure.
Brinell hardness	4,5 kp
Gross density	0,69 g   cm³

## 1-Strip Country House Flooring ASH steamed Emotion "Nizza"

softly brushed, mocca brown oil | wax

### Surfaces

- Oil | wax oxidative dried
- Mocca brown colour



Symbol picture - may vary in colour and structure

Sorting guidelines	Emotion
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	not allowed
Healthy heartwood	not allowed
Cracks	not allowed
Curled spots   differences in structure	allowed
Natural differences in colour	allowed
Natural fiber orientation	allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	not allowed

Technical data	
Thickness:	15 mm <span style="background-color: #e0e0e0;">Useful layer: approx. 5 mm</span>
Width:	150 mm
Length:	Lengthsystem 6 layers 1900 mm (8 layers   pkg.) 2 layers 950 mm*
Connection:	Tongue and groove <small>One layer 950 mm consists of 2 boards*</small>
<span style="border: 1px solid black; padding: 2px;">m²   pkg. 2,28</span>	<span style="border: 1px solid black; padding: 2px;">m²   pal. 111,72</span>
<span style="border: 1px solid black; padding: 2px;">kg   pkg. 23</span>	<span style="border: 1px solid black; padding: 2px;">kg   pal. 1127</span>
<input checked="" type="checkbox"/> Floating laying <input checked="" type="checkbox"/> Glued laying <input checked="" type="checkbox"/> Suitable for underfloor heating <small>when gluing the entire area with solvent-free adhesives</small>	



Woodtype	<b>ASH</b>
Description	3 layers of the same hardwood. The Ash with heartwood is varnished in a techno grey colour. Thus, a modern and vivid look is created. The sorting Design is slightly to very knotty, with a lively structure.
Brinell hardness	4,5 kp
Gross density	0,69 g   cm³

## 1-Strip Country House Flooring ASH Design "Ingolstadt" techno grey



### Surfaces

- Varnished 7-times
- Techno grey colour



Symbol picture - may vary in colour and structure

Sorting guidelines	Design
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	allowed
Healthy heartwood	allowed
Cracks	allowed (partly filled)
Curled spots   differences in structure	allowed
Natural differences in colour	allowed
Natural fiber orientation	allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	not allowed

Technical data					
Thickness:	15 mm <span style="background-color: #e0e0e0;">Useful layer: approx. 5 mm</span>				
Width:	150 mm				
Length:	Lengthsystem 6 layers 1900 mm (8 layers   pkg.) 2 layers 950 mm*				
Connection:	Tongue and groove <small>One layer 950 mm consists of 2 boards*</small>				
<table border="0" style="width: 100%;"> <tr> <td style="border: 1px solid black; padding: 5px;">m²   pkg. 2,28</td> <td style="border: 1px solid black; padding: 5px;">m²   pal. 111,72</td> </tr> <tr> <td style="border: 1px solid black; padding: 5px;">kg   pkg. 23</td> <td style="border: 1px solid black; padding: 5px;">kg   pal. 1127</td> </tr> </table>		m²   pkg. 2,28	m²   pal. 111,72	kg   pkg. 23	kg   pal. 1127
m²   pkg. 2,28	m²   pal. 111,72				
kg   pkg. 23	kg   pal. 1127				
<input checked="" type="checkbox"/> Floating laying <input checked="" type="checkbox"/> Glued laying <input checked="" type="checkbox"/> Suitable for underfloor heating <small>when gluing the entire area with solvent-free adhesives</small>					



Woodtype **ASH HEARTWOOD**

Description 3 layers of the same hardwood. Due to the brushing and the special treatment with oil | wax pearl white, the Core Ash with heartwood receives a white to brownish colour. The sorting Design is slightly to very knotty, with a lively structure.

Brinell hardness 4,5 kp  
 Gross density 0,69 g | cm<sup>3</sup>

## 1-Strip Country House Flooring ASH Heartwood Design "Krems"



brushed, bevel, pearl white oil | wax

### Surfaces

- Oil | wax oxidative dried
- Brushed
- Bevel 2 mm (4-sides)
- Pearl white colour



Symbol picture - may vary in colour and structure

Sorting guidelines	Design
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	allowed
Healthy heartwood	allowed
Cracks	allowed (partly filled)
Curled spots   differences in structure	allowed
Natural differences in colour	allowed
Natural fiber orientation	allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	not allowed

Technical data					
Thickness:	15 mm <span style="float: right;">Useful layer: approx. 5 mm</span>				
Width:	150 mm				
Length:	Lengthsystem 6 layers 1900 mm (8 layers   pkg.) 2 layers 950 mm*				
Connection:	Tongue and groove <small>One layer 950 mm consists of 2 boards*</small>				
<table border="0" style="width: 100%;"> <tr> <td style="border: 1px solid black; padding: 5px;">m<sup>2</sup>   pkg. 2,28</td> <td style="border: 1px solid black; padding: 5px;">m<sup>2</sup>   pal. 111,72</td> </tr> <tr> <td style="border: 1px solid black; padding: 5px;">kg   pkg. 23</td> <td style="border: 1px solid black; padding: 5px;">kg   pal. 1127</td> </tr> </table>		m <sup>2</sup>   pkg. 2,28	m <sup>2</sup>   pal. 111,72	kg   pkg. 23	kg   pal. 1127
m <sup>2</sup>   pkg. 2,28	m <sup>2</sup>   pal. 111,72				
kg   pkg. 23	kg   pal. 1127				
<input checked="" type="checkbox"/> Floating laying <input checked="" type="checkbox"/> Glued laying <input checked="" type="checkbox"/> Suitable for underfloor heating <small>when gluing the entire area with solvent-free adhesives</small>					



Woodtype	<b>ASH steamed</b>
Description	3 layers of the same hardwood. The Ash receives a slightly reddish brown colour due to the steaming with vitalized Grander water and the heartwood lends the parquet a natural appearance. The sorting Design is slightly to very knotty, with a lively structure.
Brinell hardness	4,5 kp
Gross density	0,69 g   cm³

## 1-Strip Country House Flooring ASH steamed Design "Telfs"



### Surfaces

- Oil | wax oxidative dried
- Varnished 7-times
- Untreated sanded
- Brushed
- Bevel
- Special colour

### Also available as

- System board  
(Fixed length 1100 mm)



Symbol picture - may vary in colour and structure

Sorting guidelines	Design
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	allowed
Healthy heartwood	allowed
Cracks	allowed (partly filled)
Curled spots   differences in structure	allowed
Natural differences in colour	allowed
Natural fiber orientation	allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	not allowed

Technical data					
Thickness:	15 mm <span style="background-color: #e0e0e0;">Useful layer: approx. 5 mm</span>				
Width:	150 mm				
Length:	Lengthsystem 6 layers 1900 mm (8 layers   pkg.) 2 layers 950 mm*				
Connection:	Tongue and groove <small>One layer 950 mm consists of 2 boards*</small>				
<table border="0" style="width: 100%;"> <tr> <td style="border: 1px solid black; padding: 5px;">m²   pkg. 2,28</td> <td style="border: 1px solid black; padding: 5px;">m²   pal. 111,72</td> </tr> <tr> <td style="border: 1px solid black; padding: 5px;">kg   pkg. 23</td> <td style="border: 1px solid black; padding: 5px;">kg   pal. 1127</td> </tr> </table>		m²   pkg. 2,28	m²   pal. 111,72	kg   pkg. 23	kg   pal. 1127
m²   pkg. 2,28	m²   pal. 111,72				
kg   pkg. 23	kg   pal. 1127				
<ul style="list-style-type: none"> <li><input checked="" type="checkbox"/> Floating laying</li> <li><input checked="" type="checkbox"/> Glued laying</li> <li><input checked="" type="checkbox"/> Suitable for underfloor heating <small>when gluing the entire area with solvent-free adhesives</small></li> </ul>					



Symbol picture - may vary in colour and structure



Woodtype	<b>ASH</b>
Description	3 layers of the same hardwood. The Ash without heartwood has a light yellow to brownish colour. The sorting Klassiker is essentially knot-free*, with a simple structure.
Brinell hardness	4,5 kp
Gross density	0,69 g   cm <sup>3</sup>

## 2-Strip Plank Flooring ASH "Klassiker"



### Surfaces


- Oil | wax oxidative dried
- Varnished 7-times
- Untreated sanded
- Brushed
- Bevel
- Special colour



Symbol picture - can vary in colour and structure

Sorting guidelines	Klassiker
Healthy knots	fill ø 5 mm allowed
Black knots	fill ø 5 mm allowed
Healthy red heart	not allowed
Healthy heartwood	not allowed
Cracks	not allowed
Curled spots   differences in structure	scattered allowed
Natural differences in colour	slightly allowed
Natural fiber orientation	scattered allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	not allowed
Stains from storage and light blueness	not allowed
Knocked spots	not allowed
Mirror	not allowed

Technical data					
Thickness:	15 mm <span style="background-color: #e0e0e0;">Useful layer: approx. 5 mm</span>				
Width:	140 mm				
Length:	Fixed length 2400 mm (8 layers   pkg.)				
Connection:	Tongue and groove				
<table border="1" style="width: 100%;"> <tr> <td>m<sup>2</sup>   pkg. 2,69</td> <td>m<sup>2</sup>   pal. 112,98</td> </tr> <tr> <td>kg   pkg. 26,2</td> <td>kg   pal. 1104</td> </tr> </table>		m <sup>2</sup>   pkg. 2,69	m <sup>2</sup>   pal. 112,98	kg   pkg. 26,2	kg   pal. 1104
m <sup>2</sup>   pkg. 2,69	m <sup>2</sup>   pal. 112,98				
kg   pkg. 26,2	kg   pal. 1104				
<input checked="" type="checkbox"/> Floating laying <input checked="" type="checkbox"/> Glued laying <input checked="" type="checkbox"/> Suitable for underfloor heating <span style="font-size: small;">when gluing the entire area with solvent-free adhesives</span>					



Woodtype	<b>ASH</b>
Description	3 layers of the same hardwood. The Ash with heartwood has a light yellow to slightly brownish to prominent dark brown colour. The sorting Trend-Epoca is knotty, with a lively structure.
Brinell hardness	4,5 kp
Gross density	0,69 g   cm <sup>3</sup>

## 2-Strip Plank Flooring ASH "Trend-Epoca"



### Surfaces


- Oil | wax oxidative dried
- Varnished 7-times
- Untreated sanded
- Brushed
- Bevel
- Special colour



Symbol picture - may vary in colour and structure

Sorting guidelines	Trend-Epoca
Healthy knots	allowed (partly filled)
Black knots	allowed (partly filled)
Healthy red heart	allowed
Healthy heartwood	allowed
Cracks	allowed (partly filled)
Curled spots   differences in structure	allowed
Natural differences in colour	allowed
Natural fiber orientation	allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	allowed
Stains from storage and light blueness	allowed
Knocked spots	not allowed
Mirror	not allowed

Technical data					
Thickness:	15 mm				
Width:	140 mm				
Length:	Fixed length 2400 mm (8 layers   pkg.)				
Connection:	Tongue and groove				
<table border="0" style="width: 100%;"> <tr> <td style="border: 1px solid black; padding: 5px;">m<sup>2</sup>   pkg. 2,69</td> <td style="border: 1px solid black; padding: 5px;">m<sup>2</sup>   pal. 112,98</td> </tr> <tr> <td style="border: 1px solid black; padding: 5px;">kg   pkg. 26,2</td> <td style="border: 1px solid black; padding: 5px;">kg   pal. 1104</td> </tr> </table>		m <sup>2</sup>   pkg. 2,69	m <sup>2</sup>   pal. 112,98	kg   pkg. 26,2	kg   pal. 1104
m <sup>2</sup>   pkg. 2,69	m <sup>2</sup>   pal. 112,98				
kg   pkg. 26,2	kg   pal. 1104				
<ul style="list-style-type: none"> <li><input checked="" type="checkbox"/> Floating laying</li> <li><input checked="" type="checkbox"/> Glued laying</li> <li><input checked="" type="checkbox"/> Suitable for underfloor heating when gluing the entire area with solvent-free adhesives</li> </ul>					



Woodtype	<b>ASH steamed</b>
Description	3 layers of the same hardwood. Due to the steaming with vitalized Grander water, the Ash without heartwood receives a brown colour. The sorting Trend-Epoca is knotty with a lively structure and heartwood.
Brinell hardness	4,5 kp
Gross density	0,69 g   cm³

## 1-Strip Plank Flooring ASH steamed "Trend-Epoca"



### Surfaces

- Oil | wax oxidative dried
- Varnished 7-times
- Untreated sanded
- Brushed
- Bevel
- Special colour

Symbol picture - can vary in colour and structure

Sorting guidelines	Trend-Epoca
Healthy knots	fill Ø 5 mm allowed
Black knots	fill Ø 5 mm allowed
Healthy red heart	not allowed
Healthy heartwood	not allowed
Cracks	not allowed
Curled spots   differences in structure	partly allowed
Natural differences in colour	partly allowed
Natural fiber orientation	partly allowed
Wormholes & insect-ate-spots	not allowed
Sapwood	not allowed
Red or brown spots	not allowed
Stains from storage and light blueness	not allowed
Knocked spots	not allowed
Mirror	not allowed

Technical data					
Thickness:	15 mm				
Width:	140 mm				
Length:	Lengthsystem: 2400 mm (8 layers   pkt.)				
Connection:	Tongue and groove				
<table border="1" style="width: 100%;"> <tr> <td>m²   pkt. 2,69</td> <td>m²   pal. 112,98</td> </tr> <tr> <td>kg   pkt. 26,2</td> <td>kg   pal. 1104</td> </tr> </table>		m²   pkt. 2,69	m²   pal. 112,98	kg   pkt. 26,2	kg   pal. 1104
m²   pkt. 2,69	m²   pal. 112,98				
kg   pkt. 26,2	kg   pal. 1104				
<input checked="" type="checkbox"/> Floating laying <input checked="" type="checkbox"/> Glued laying <input checked="" type="checkbox"/> Suitable for underfloor heating when gluing the entire area with solvent-free adhesives					

