

Woodtype	BIRCH
Description	3 layers of the same hardwood. The Birch without heartwood has a light, wheaten colour with distinctive colour inclusions. The sorting Wohngefühl is knotty, with a medium structure.
Brinell hardness Gross density	2,8 kp 0,65 g cm³

## 1-Strip Country House Flooring BIRCH Wohngefühl "Innsbruck"



## Surfaces

- ✓ Oil | Wax oxidative dried
- ✓ Varnished 7-times
- ✓ Untreated sanded
- ✓ Bevel




Symbol picture - may vary in colour and structure

Sorting guidelines	Wohngefühl		
Healthy knots	allowed (partly filled)		
Black knots	to approx. 35 mm allowed (partly filled)		
Healthy red heart	not allowed		
Healthy heartwood	not allowed		
Cracks	scattered allowed (partly filled)		
Curled spots   differences in structure	scattered allowed		
Natural differences in colour	allowed		
Natural fiber orientation	to 1   3 allowed		
Wormholes & insect-ate-spots	not allowed		
Sapwood	not allowed		
Red or brown spots	scattered allowed		
Stains from storage and light blueness	not allowed		
Knocked spots	not allowed		
Mirror	not allowed		

Technical data					
Thickness: 15 mm	Useful layer: approx. 5 mm				
Width: 150 mm	, , , , , , , , , , , , , , , , , , , ,				
Length: Lengthsyste	em 6 layers 1900 mm				
(8 layers   pkg.) 2 layers 950 mm*					
Connection: Tongue and	groove				
One layer 950 mm consists of 2 boards*					
m² pkg. 2,28	m² pal. 111,72				
kg pkg. 23	kg pal. 1127				
<ul><li>Floating laying</li><li>Glued laying</li><li>Suitable for underfl</li></ul>	oor heating				

when gluing the entire area with solvent-free adhesives



Symbol picture - may vary in colour and structure



Woodtype	BIRCH
Description	3 layers of the same hardwood. The Birch without heartwood has a light, wheaten colour with distinctive colour inclusions. The sorting Klassiker is essentially knot-free*, with a simple structure.
Brinell hardness	2,8 kp

## 2-Strip Plank Flooring BIRCH "Klassiker"

0,65 g | cm<sup>3</sup>

## Surfaces

Gross density

- ✓ Oil | Wax oxidative dried
- ✓ Varnished 7-times
- ✓ Untreated sanded
- ✓ Bevel



Sorting guidelines	Klassiker	
Healthy knots	till ø 5 mm allowed	
Black knots	till ø 5 mm allowed	
Healthy red heart	not allowed	
Healthy heartwood	not allowed	
Cracks	not allowed	
Curled spots   differences in structure	allowed	
Natural differences in colour	slightly allowed	
Natural fiber orientation	scattered allowed	
Wormholes & insect-ate-spots	not allowed	
Sapwood	not allowed	
Red or brown spots	not allowed	
Stains from storage and light blueness	not allowed	
Knocked spots	not allowed	
Mirror	not allowed	

$\sim$	 ical	 $\sim$	ı

Thickness: 15 mm Useful layer: approx. 5 mm

Width: 140 mm

Length: Fixed length 2400 mm

(8 layers | pkg.)

Connection: Tongue and groove

m<sup>2</sup> | pkg. 2,69 m<sup>2</sup> | pal. 112,98

kg|pkg. 26,2 kg|pal. 1104

Floating laying

Glued laying

Suitable for underfloor heating when gluing the entire area with solvent-free adhesives

